



# Plasto-Mend TPO Adhesion Promoter

## 1021, 1025

**Plasto-Mend TPO Adhesion Promoter is a chemical bonding prep formulated for the repair and refinishing of problem plastics. It has a unique blend of chlorinated polyolefins to promote adhesion of coatings and repair materials to PP (Polypropylene), PE (Polyethylene), TPO (Thermoplastic Olefins), and most difficult to bond plastics.**



### Mix Ratio

Ready to use



### Suitable Substrates

- Raw plastic - rigid (SMC, BMC)
- Raw plastic - flex (ABD, PPO)
- Raw plastic - soft (PUR)

*Note: Due to the diverse nature of plastics, always test plastic substrate for acceptable adhesion. Adhesion promoter maybe required for proper adhesion.*

*Note: Test pre-primed panels with acetone or paint thinner. If coating fails, strip panel to bare plastic & follow SOP 251 for Raw Plastic.*



### Surface Prep & Application

Clean parts thoroughly using a plastic cleaner such as Transtar's SCAT 6311, Speedi SCAT 6321, Aqua SCAT 1391/1394 or Scuff & Prep Paste 6338 with a scuff pad to enhance the performance of the repair material.

Plasto-Mend TPO Adhesion Promoter is used for all repairs and refinishing of PP, PE, and TPO plastics. Apply Plasto-Mend TPO Adhesion Promoter in one light even coat. Allow to dry 10 - 15 minutes before priming, applying of repair material, or topcoating.

*Note: For best results, do not apply more than one coat. NOT FOR USE ON SMC, ABS OR PULSE PLASTICS.*



### Flash Times/Dry Times


To prime ..... 10 - 15 min



### Gun Set-up

Siphon feed ..... 1.2 - 1.6 mm  
 Pressure feed ..... 1.0 - 1.2 mm

Gravity feed ..... 1.2 - 1.4 mm  
 HVLP/LVLP ..... 1.2 - 1.5 mm



**Air Pressure**

Siphon feed.....	35 - 45 psi	Gravity feed (@ regulator).....	25 - 35 psi
Pressure feed .....	40 - 50 psi	HVLP/LVLP (@ aircap).....	10 psi

**Fluid Pressure**

Pressure feed .....8 - 10 psi



**Product Specifications**

Color.....	Pale yellow	Size (1021).....	Gallon
Shelf life.....	3 years	(1025).....	5 Gallon

**Regulatory**

Category.....	Adhesion promoter	Wt % of volatiles.....	94.51
VOC actual.....	5.48#/gal (656 g/l)	Wt % of water .....	0
VOC regulatory.....	6.19#/gal (742g/l)	Wt % of exempt compound .....	11.5
Density.....	6.60 #/gal	Vol % of exempt compound .....	11.48



**Limitations & Precautions**

- Visit [www.tat-co.com](http://www.tat-co.com) to assure use of the most current instructions and TDS on this product.
- See website ([www.tat-co.com](http://www.tat-co.com)) for this document in other languages. (Vea el web site para este documento en español. Voir le site web pour ce document en français.)
- For use only by professional, trained painters. Not for sale to or use by the general public.

**LIMITED WARRANTY**

The successful performance of this product is dependent on many factors beyond our control. Results are dependent upon the skill of the operator. This product is manufactured to meet the highest level of consistency and quality for the intended use. Transtar Autobody Technologies, Inc. warrants that its products meet the specifications which it sets for them. Should this product be proven to be off-specification within shelf life as stated in this datasheet, Transtar Autobody Technologies, Inc. will, at its sole discretion, either replace the product or issue credit for the original purchase price of the product. The replacement or refund shall be the buyer's sole remedy and Transtar Autobody Technologies, Inc. and its affiliates MAKE NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, DESIGN COMPATIBILITY AND FITNESS FOR A PARTICULAR PURPOSE. LABOR OR COST OF LABOR AND OTHER INCIDENTAL AND/OR CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED. The technical data contained herein are true and accurate to the best of our knowledge. Published technical data and instructions are subject to change without prior notice.