



PRODUCT DATA

6216

Jammin' Blender

DESCRIPTION:

Jammin' Blender is designed to aid in the blending of metallic, pearl and tri-coat urethane basecoat colors; it can also be used as fast drying cut in clear and an inter-coat clear for tape outs of two tones and multi-color graphics. Jammin' Blender is UV stable and ready to spray.

TECHNICAL DATA:

APPEARANCE:	Water white clear
VOC AS PACKAGED:	5.89 #/gal (705 g/l)
DENSITY:	7.09 #/gal
% SOLIDS:	14%

SURFACE PREPARATION:

Please refer to Basecoat Manufacturer's Data Sheet for surface preparation instructions.

APPLICATION AND MIXING:

Blending

Apply 1 - 2 coats of Jammin' Blender to the prepared blend panels allow a 10 - 15 minutes flash before the application of basecoat. Apply 2 - 3 coats of basecoat to the replacement panels/ repair areas or until hiding. Extend each coat slightly beyond the first and taper each coat, allow proper flash time between coats. Refer to Basecoat Manufacturer's Data Sheet for specific reduction and application instructions. Mix 2 parts of 6216 with 1 part of ready to spray basecoat and apply 1 - 2 coats over the blend area. Allow 10 - 15 flash time and apply desired Transtar Clearcoat.

Inter-coat Clear

If necessary follow the instructions above. Allow color to flash 10 - 15 minutes. Apply 1 - 2 coats of Jammin' Blender to the entire panel allow a 15 - 20 minutes dry time before applying masking tape for two-tone or graphics.

Cut in Clear

Allow color to flash 10 - 15 minutes. Apply 2 - 3 coats of Jammin' Blender allow 15 - 20 minutes before handling/assembly. To increase gloss additional coats may be applied up to a maximum of 6 coats.

SALES POINTS:

- Helps produce an invisible repair
- Aids in metallic/pearl control on blends
- Speeds up multi-color refinish process
- Ready to spray

COMPETITION:

Dupont 69301S	DBU500	Standex 11514 (1litre) or 16150 (2.5 litre) Basecoat Colorless
Glasurit 55-B500	Sherwin Williams S63	Lesonal 070166
Nexa P273-1051	Sikkens Basefix	
PPG DBC500	Car System 126.025	

(Refer to Material Safety Data Sheet for proper handling of products listed in this bulletin.)

PACKAGE SIZES:

#6216 Jammin' Blender, 2.5 Liter, 2/case

DISCLAIMER: The technical information and suggestions for use have been compiled for your guidance and usage. Such information is based on Transtar Autobody Technologies experience and research and is believed to be reliable. As Transtar has no control over conditions in which the product is used, stored, or otherwise handled, the above information does not constitute a warranty. Buyers must assume responsibility for the suitability of the product for their purposes.

TRANSTAR AUTOBODY TECHNOLOGIES • 2040 HEISERMAN DRIVE, BRIGHTON, MI 48114 • (800) 824-2843

FAX (800) 477-7923 • EMAIL: info@tat-co.com

