

Technical Data Sheet

Transtar's MAX Clearcoat is a fast drying clearcoat that provides the additional features of low overspray and super high gloss. This unique product improves production by maximizing vehicle throughput. The fast flash feature provides the benefit of less dust and dirt getting trapped in the finish, which means less labor expanded to buff or polish.

SUITABLE SUBSTRATES

Substrate		Substrate		Substrate	
Solvent-borne Basecoat	✓	Waterborne Basecoat	✓	Acrylic Lacquer	
1K Enamel		2K Enamel	✓		
OEM Finish & Old Paint Work - Reversible		OEM Finish & Old Paint Work - Non-Reversible	✓		

MIXING



By Volume: 4 parts 7761-MTR/7764-MTR MAX Clearcoat
1 part 6800 Series Activators
Optional: Up to 5% 6700 or 6700-F Series Urethane Grade Reducer*

Pot Life 2-4 hours (@70°F (21°C) and 50% relative humidity)

* Use reducer according to shop conditions. Using reducers other than Zero VOC Urethane Grade Reducers will increase VOC.

FLASH TIMES/DRY TIMES



Flash Between Coats 2-15 minutes
Dust Free 5-25 minutes
Dry to Sand 1-2 hours
Delivery 2-3 hours
Force Drying 15 minutes @ 140°F (25°C) immediately without purging

Activator	Flash Time	Dust Free
6854 Lightning	2 min	10 min
6874/6877 Spot & Panel	3-5 min	5-10 min
6894 Overall	5-10 min	10-15 min
6894HT/6897HT Hi Temp	10-15 min	15-25 min

SURFACE PREPARATION



Tack surface thoroughly before application.

SPRAY GUN SET-UP/APPLICATION



Gun Type HVLP/LVLP Gravity Feed
Fluid Tip 1.2 - 1.4 1.2 - 1.6
Air Pressure 10 PSI @ aircap 25 - 35 PSI @ gun
Mil Thickness: 2-3 coats (@ 1.2 mils per coat dry film thickness). Must have a minimum of 2.2 mils.

LIMITATIONS & PRECAUTIONS

- For use only by professional, trained painters. Not for sale to or use by the general public.
- Before use, read and follow all TDS, label and SDS precautions.
- See next page for more detailed production application.

Technical Data Sheet

SPRAY GUN SET-UP

Gun Type	Siphon Feed	Gravity Feed	Pressure Feed	HVLP/LVLP
Fluid Tip	1.4-1.6 mm	1.2-1.6 mm	1.0-1.2 mm	1.2-1.6 mm
Air Pressure	35-45 PSI (@gun)	25-35 PSI (@ gun)	40-50 PSI (@ gun)	10 PSI (@ aircap)
Fluid Pressure	N/A	N/A	8-10 PSI	N/A

Always refer to gun manufacturer's recommendation for proper set up and spray pressure.

SURFACE PREPARATION

Tack thoroughly before application.

For blending clearcoat refer to SOP #513 and # 514.

ADDITIVES

Additives: Kicker (6417) - Can be used in temperatures BELOW 65°F (24°C) at ¼ oz. per sprayable quart.
 Appearance Improver (6487) - Can be used at a rate of 1-2 oz per sprayable quart.
 Fisheye Remover (6737) - Can be used at a rate of ½ oz per sprayable quart.
 Universal Urethane Flex Additive (9194) - Use with soft, flexible substrates. Refer to TDS for mixing information.

APPLICATION & FILM BUILD

Apply 2 - 3 flowing coats using the spray gun setting listed above. Flash for 2 – 15 minutes depending on activator used (refer to flash/dry times on page one). Keep spray gun nozzle 6 - 10 inches from the vehicle to avoid entrapment of air in paint film. Always keep containers tightly closed to prevent moisture contamination. Clean equipment thoroughly after use.

Critical Recoat Time: Do not flash for more than 45 minutes between coats. If more than 45 minutes @ 70°F (21°C) is reached, wait at least 5 hours before applying more clear or basecoat. Lightly scuff surface and degrease before application.

Film Build: 2-3 coats @ 1.2 mils. Must have a minimum of 2.2 mils and not to exceed 3.6 mils.

PRODUCT SPECIFICATIONS

Weight per gallon: 7.59	Shelf Life: 1 year
RTS Solids by Weight: 39%	Color: Clear Liquid
Approximate Coverage: 512 ft ² /gal @ 1 mil	Size: Gallon (7761-MTR), Quart (7764-MTR)

REGULATORY

Category: Clearcoat	7761-MTR/7764-MTR	6854	6874/6877	6894	6894HT
VOC Actual	3.65#/gal (437 g/l)	3.5#/gal (420 g/l)	3.4#/gal (407 g/l)	3.52#/gal (422 g/l)	3.5#/gal (419 g/l)
VOC Regulatory	4.47#/gal (536 g/l)	3.63#/gal (437 g/l)	3.72#/gal (446 g/l)	3.63#/gal (435 g/l)	3.65#/gal (438 g/l)
Weight % of Volatiles	64.25	46.98	49.93	46.20	46.20
Weight % of Water	0	0	0	0	0
Weight % of Exempt Compounds	16.13	5.20	11.00	4.00	5.50
Volume % of Exempt Compounds	18.36	3.92	8.62	3.00	4.25
Density of Material #/gal	7.59	8.37	8.73	8.34	8.59
		with 6854	with 6874/6877	with 6894	with 6894HT
Ready to Use (less water, less exempt compounds)		4.28#/gal (513 g/l)	4.31#/gal (516 g/l)	4.28#/gal (513 g/l)	4.29#/gal (514 g/l)

Visit www.tat-co.com to assure you are using most updated TDS, to view in other languages and for links to Standard Operating Procedures (SOPs).

TRANSTAR AUTOBODY TECHNOLOGIES • 2040 HEISERMAN DRIVE, BRIGHTON, MI 48114 • (800) 824-2843

FAX (800) 477-7923 • EMAIL: info@tat-co.com