

Technical Data Sheet

Motor City Euro Clearcoat (4.2 VOC) is an acrylic urethane clearcoat that is suitable for all automotive refinishing as well as trucks and equipment. It can be used with all solvent and water based basecoats.

SUITABLE SUBSTRATES

Substrate		Substrate		Substrate	
Solvent-borne Basecoat	✓	Waterborne Basecoat	✓	Acrylic Lacquer	
1K Enamel		2K Enamel	✓		
OEM Finish & Old Paint Work - Reversible		OEM Finish & Old Paint Work - Non-Reversible	✓		

MIXING



By Volume: 2 parts 8121 Motor City Euro Clearcoat
 1 part 8136/8146 Motor City Euro Activators
 Optional: Up to 5% 6700 or 6700-F Series Urethane Grade Reducer*

Pot Life 3 hours (@70°F (21°C) and 50% relative humidity)

* Use reducer according to shop conditions. Using reducers other than Zero VOC Urethane Grade Reducers will increase VOC.

FLASH TIMES/DRY TIMES



Flash Between Coats 5-20 minutes
 Dust Free 15-40 minutes
 Dry to Sand 8 hours
 Delivery 12 hours MIN
 Force Drying 40 minutes @ 140°F (60°C) after a 15 minute flash

Activator	Flash Time	Dust Free
8136 Fast	5-10 min	15-25 min
8146 Slow	15-20 min	30-40 min

SURFACE PREPARATION



Tack surface thoroughly before application.

SPRAY GUN SET-UP/APPLICATION



Gun Type HVLP/LVLP Gravity Feed
 Fluid Tip 1.2 - 1.4 1.2 - 1.4
 Air Pressure 10 PSI @ aircap 35 - 45 PSI @ gun inlet
 Mil Thickness: 1.2 mil per coat (dry film thickness) Must have a minimum of 2.2 mils and not to exceed 3.6 mils.

LIMITATIONS & PRECAUTIONS

- For use only by professional, trained painters. Not for sale to or use by the general public.
- Before use, read and follow all TDS, label and SDS precautions.
- See next page for more detailed production application.

Technical Data Sheet

SPRAY GUN SET-UP

Gun Type	Siphon Feed	Gravity Feed	Pressure Feed	HVLP/LVLP
Fluid Tip	1.4-1.6 mm	1.2-1.4 mm	1.0-1.2 mm	1.2-1.4 mm
Air Pressure	35-45 PSI (@gun)	25-35 PSI (@ gun)	40-50 PSI (@ gun)	10 PSI (@ aircap)
Fluid Pressure	N/A	N/A	8-10 PSI	N/A

Always refer to gun manufacturer's recommendation for proper set up and spray pressure.

SURFACE PREPARATION

Tack thoroughly before application.
 For blending clearcoat refer to SOP #513 and # 514.

ADDITIVES

Additives: Kicker (6417) - Can be used at a rate of ¼ - ½ oz per sprayable quart.
 Appearance Improver (6487) - Can be used at a rate of 1-2 oz per sprayable quart.
 Fisheye Remover (6737) - Can be used at a rate of ½ oz per sprayable quart.
 Universal Urethane Flex Additive (9194) - Use with soft, flexible substrates. Refer to 9194 TDS for mixing information.

APPLICATION & FILM BUILD

Apply 2 - 3 flowing coats using the spray gun setting listed above. Flash for 5 – 20 minutes depending on activator used (refer to flash/dry times on page one). Keep spray gun nozzle 6 - 10 inches from the vehicle to avoid entrapment of air in paint film. Always keep containers tightly closed to prevent moisture contamination. Clean equipment thoroughly after use.

Critical Recoat Time: Do not flash for more than 1 hour between coats. If more than 1 hour @ 70°F (21°C) is reached, wait at least 6 hours before applying more clear or basecoat. After 24 hours, lightly scuff the clearcoat before applying additional material.

Film Build: 2-3 coats @ 1.2 mils. Must have a minimum of 2.2 mils and not to exceed 3.6 mils.

PRODUCT SPECIFICATIONS

Weight per gallon: 8.07	Shelf Life: 3 years
RTS Solids by Weight: 38%	Color: Clear Liquid
Approximate Coverage: 511 ft ² /gal @ 1 mil	Size: 5 Liter (8121), 2.5 Liter (8136, 8146)

REGULATORY

Category: Clearcoat	8121	8136	8146
VOC Actual	1.94#/gal (233g/l)	5.12#/gal (613 g/l)	4.90#/gal (587 g/l)
VOC Regulatory	3.29#/gal (395g/l)	5.12#/gal (613 g/l)	4.90#/gal (587 g/l)
Weight % of Volatiles	61.43	63.45	60.73
Weight % of Water	0	0	0
Weight % of Exempt Compounds	37.37	0	0
Volume % of Exempt Compounds	41.11	0	0
Density of Material #/gal	8.07	8.07	8.07
		with 8136	with 8146
Ready to Use (less water, less exempt compounds)		4.13#/gal (495 g/l)	4.03#/gal (483 g/l)